

1. Product Name

EnergyGuard® Butyl Elastomeric Roof Coating

2. EPDM Coatings

P.O Box 3429,
Wernersville PA 19609,
EPDM Coatings N.E Sales Office,
494 Bridgeport Ave Suite 101,
PMB 342 Shelton,
CT 06484-4748
URL: www.epdmcoatings.net

3. Product Description

EnergyGuard® Butyl Elastomeric Roof Coating is a solvent based, waterproof, butyl rubber roof coating for all types of roofs.

Basic Uses

Built Up Roofing (BUR),
Concrete Roofs, Metal Roofs,
Modified Bitumen, Polyurethane
Foam, Single Ply Roofing (PVC,
TPO).

Advantages

- Provides a seamless, durable membrane.
- Acts as a protective vapor barrier to most substrates.
- Withstands ponding conditions in low slope roofs.
- Excellent elongation properties.
- Superior adhesion to various substrates.
- Contains fungicides and mildewcides.
- Heat reflective coating helps reduce cooling costs.
- Reflects the sun's UV-rays and prevents premature degradation.
- Prevents premature roof failure by controlling thermal cycling.



4. Technical Data

See table on the following page.

5. Installation

- This product is a vapor barrier and must be installed on a clean, oil-free and dry substrates only. A moisture survey may be needed.
- Any existing coating must be checked for good adhesion.
- Before application, any loosely adhered coating must be removed and bare surfaces must be prepared, cleaned and checked for compatibility.
- EnergyGuard® Butyl Elastomeric Roof Coating is ready to use. Thinning is not recommended.
- Containers should not be left open for extended periods of time.
- Follow our roof repair and roof restoration procedures and always perform a coating adhesion test before doing the entire roof.
- **Spray:** Airless Sprayer, 1gpm, 3,000 psi, .025 or .031 tip.
- **Brush:** Good quality synthetic bristle brush.
- **Roller:** Long nap roller.
- **Clean Up:** Xylene.*

6. Availability & Cost

EnergyGuard® Butyl Elastomeric Roof Coating is available directly from EPDM Coatings and from online distributors. Contact EPDM Coatings for pricing information.

7. Warranty

On preapproved, qualified applications, using EPDM approved applicators, a 10 year warranty is available. Contact EPDM Coatings for complete warranty information.

8. Maintenance

Periodic maintenance of EPDM Roof Restoration System ensures extended service life and maintains reflectivity.

9. Technical Services

Contact EPDM Coatings for Technical Support. Additional information, product literature, brochures, and specifications are available.

10. Filing Services

Additional product information is available from EPDM Coatings.



EnergyGuard® Butyl Elastomeric Roof Coating Technical Data

Property	Value	Test Method
Color	White or any custom color	
Viscosity	2000 – 2500 cps	Brookfield
Solids by weight	40% ± 2%	
Solids by volume	45% ± 2%	
Density	7 ± .2 lbs per gallon	
Hardness	45 Shore A	ASTM D-2240
Tensile Strength	1000 ± 100 psi	ASTM D-412
Permeability	< 1.11 g/s* m ² *pa	ASTM E-96
Elongation	900%	ASTM D-412
Flash Point	68°F	
Coverage	1.5 – 2.0 gal/100 s.f. per coat. 2 coats recommended.	
Application Temperature	45°F (and rising) – 95°F, Less than 85% relative humidity.	
Dry Time	Dry to touch in 3 – 4 hours, 4 – 10 hours to recoat.	
Shelf Life	6-8 months @ 40°-90°F	
Clean Up	Xylene	
VOC	517 g/lit	

Freight Classification: Paint – Flammable Liquid (UN 1263 Red Label Required)

Warning: EnergyGuard® Butyl Elastomeric Roof Coating contains Xylene, VM – P Naptha. Keep away from open flame, heat or sparks. Use only in ventilated areas and provide mechanical ventilation in enclosed spaces. Avoid breathing vapor or mist. Approved (MESA/NIOSH) chemical respirator and protective clothing must be used at all times. Fresh air hose masks required for interior applications. EPDM Coatings must be completely dry before exposing to water or foot traffic. Keep EPDM Coatings containers covered when not in use. Dispose of all containers in accordance with state and local environmental regulations. Keep away from children. If ingested, DO NOT induce vomiting. Call Physician immediately.

Product information contained herein are presented in good faith and believed to be reliable. They do not constitute part of our terms and conditions of sale. It is also not a guarantee, either expressed or implied, that the data are correct or that products described are merchantable or fit for a particular purpose as methods of use are beyond our control. Customer should determine the suitability of our materials and installation recommendations before usage. Manufacturer's sole responsibility shall be to replace that portion of any product that proved to be defective.



This product data sheet conforms to the editorial style prescribed by The Construction Specifications Institute. The manufacturer is responsible for technical accuracy.